



Classic

GENERAL SPECIFICATIONS

Overall Composition	80% PVC / 20% Polyester
Surface Composition	100% PVC (Phthalate Free)
Backing Composition	100% Polyester
Weight	30.0 oz. Per Linear Yard 663.2 gsm
Width	54"
Thickness	1.20 mm
Direction	Non-Directional

PERFORMANCE SPECIFICATIONS

Abrasion Resistance	500,000+ Double Rubs*	ASTM D4157-13
Stain Resistance	Yes, PFAS-free	
Bleach Resistance	Yes, 10% Dilution	
Breaking Strength	Warp: 115 / Fill: 102	ASTM D751-06(2011)
Coating Adhesion	Warp: 5.0 / Fill: 4.9	ASTM D751-06(2011)
Cold Crack	-20° F	CFFA-6a-2007
Colorfastness to Light	Class 4.5 / 1,000 Hours	AATCC 16.3-2014, Opt 3
UV Resistance	Class 4.0 / 1,000 Hours	ASTM G154-12a
Crocking Resistance	Dry: 5.0 / Wet: 5.0	AATCC 8-2007
Elongation	Warp: 43.1% / Fill: 82.5%	ASTM D5034-09(2013)
Flex Resistance	25,000+	ASTM D2907-03(2010)
Mildew Resistance	Pass	ASTM G21-13
Sulfide Stain Resistance	Yes	
Seam Strength: Tack Tear	Warp: 51.68 / Fill: 47.64	ASTM D751-06(2011)
Tear Strength: Tongue Tear	Warp: 6.2 / Fill: 7.9	ASTM D751-06(2011)
Stretch and Set	Warp: Stretch 19.5% / Set 1.0% Fill: Stretch 53.3% / Set 8.3% Bias: Stretch 25.0% / Set 5.6%	SAE J855-2009



*ACT® Registered Certification Marks

**Abrasion test results exceeding ACT Performance Guidelines are not an indicator of product lifespan.*

FLAMMABILITY SPECIFICATIONS

California TB 117:13	Pass
UFAC Class I	Pass
NFPA 260	Pass
FMVSS 302	Pass

GENERAL PRODUCT INFORMATION

Country of Origin	Taiwan
HTS Code	5903.10.2090
Roll Size	30 Yards/Roll



Classic

CLEANING CODE

Cleaning Code: SW, BC

For complete cleaning information, please refer to the Cleaning and Care Guide.

REDUCED ENVIRONMENTAL IMPACT

This product does not pose any exposure risks associated with the chemicals in Prop 65

No added flame retardant chemicals – AB2998 compliant

No added anti-bacterial / anti-microbial chemicals

Phthalate free / PFAS-free

Lead / heavy metal free

BPA free / tris free / formaldehyde free

Does not contain conflict minerals

